



# KreteAir 800

An aqueous solution of Vinsol Resin designed to offer air entrainment in precast concrete products.

## Features

- Vinsol Resin Solution

## Benefits

- No Mixing Required Prior to Use
- Allows Adjustable Entrained Air Content

## Technical Information

PARAMETER	TYPICAL VALUE
Appearance	Dark brown liquid
Specific Gravity	1.036
pH	11.4

## Directions for use

1. Use at dosage rate of 30 – 375 ml per 100kg of cementitious material.
2. Add with the final batch water.
3. For Ribbon Mixers: Mix a maximum of 30 seconds. DO NOT OVER-MIX.  
For Pan Mixers: Mix a maximum of 20 seconds. DO NOT OVERMIX.
4. Check the air content of the resulting precast product.
5. If more entrained air is desired, add additional Krete Air 800 to subsequent batches until the desired air content is achieved.

## Product packaging

- Available in bulk, 1,000 litre IBCs, 210 litre drums and 25 litre jerry cans.
- Samples are available by request.

## Product storage and shelf life

- Store in dry area. Keep containers tightly closed. Do not store in excessively high temperatures (>35 C°). KEEP FROM FREEZING.
- Avoid physical damage to containers.
- Krete Air 800 has a shelf life of eight (8) months in original, unopened packaging.

For Industrial Use Only. Not for internal consumption.  
Consult SDS for safety and regulatory information.

PDS – KRETEAIR 800 – 06/2022

Excelsior Works Castle Park Flint Flintshire CH6 5NT United Kingdom  
T +44 (0) 1352 732 157 F +44 (0) 1352 735 530 E info@procterjohnson.com  
[procterjohnson.com](http://procterjohnson.com)



The information presented above is true and accurate to the best of our knowledge. No warranty or guarantee, expressed or implied is made regarding the performance of the product. This information is not intended to be all-inclusive concerning handling, storage and use of the product. Health and other regulatory factors are the responsibility of the customer.