



# RheoFalt LT-70

Synthetic paraffin. It contains an effective oxidation inhibitor.

Properties	Standard	Unit	Specification
Congealing point	DIN ISO 2207	°C	68 - 72
Penetration at 25 °C	DIN 51 579	0.1 mm	9 - 16
Oil content	DIN ISO 2908	%	max. 0.5
Viscosity at 100 °C	DIN 51 562 / T1	mm <sup>2</sup> /s	type. 5.9
Colour, Saybolt	DIN 51 411	-	min. +28
Colour	visual	-	white
Density at 70 °C	DIN 51 757	kg/m <sup>3</sup>	780
Dosage	2-4 m/m % on bitumen	-	-

For Industrial Use Only. Not for internal consumption.  
Consult SDS for safety and regulatory information.

PDS - RHEOFALT LT-70- 06/2022

Excelsior Works Castle Park Flint Flintshire CH6 5NT United Kingdom  
T +44 (0) 1352 732 157 F +44 (0) 1352 735 530 E info@procterjohnson.com  
[procterjohnson.com](http://procterjohnson.com)

 Procter Johnson

The information presented above is true and accurate to the best of our knowledge. No warranty or guarantee, expressed or implied is made regarding the performance of the product. This information is not intended to be all-inclusive concerning handling, storage and use of the product. Health and other regulatory factors are the responsibility of the customer.