



RheoFalt WKR-2

Properties	Method	Specification
Congealing point	ASTM D 3104	102 – 108 °C
Penetration at 25 °C	ASTM D 1321	0 – 4 *0.1mm
Viscosity at 160 °C	ASTM D 3236	3200 – 4000 Mpa.s
Shape	-	Pallets
Colour	Visible	Yellow / Brown
Advised mixture with Bitumen 80-100	Visual	15-20%

Effects of Bitumen

%-addition	-	50°C	26
Bitumen 80/100	-	76-80	80
Congealing point *1	25°C	> 300	1250 Mpa.s
Penetration *2	40°C	365 Mpa.s	450 Mpa.s
	140°C	140 Mpa.s	220 Mpa.s
Viscosity	160°C	70 Mpa.s	
	180°C	18	
	0	0 – 4 *0.1mm	
	100	78°C	

For Industrial Use Only. Not for internal consumption.
Consult SDS for safety and regulatory information.

PDS - RHEOFALT WKR-2- 06/2022

Excelsior Works Castle Park Flint Flintshire CH6 5NT United Kingdom
T +44 (0) 1352 732 157 **F** +44 (0) 1352 735 530 **E** info@procterjohnson.com
procterjohnson.com



The information presented above is true and accurate to the best of our knowledge. No warranty or guarantee, expressed or implied is made regarding the performance of the product. This information is not intended to be all-inclusive concerning handling, storage and use of the product. Health and other regulatory factors are the responsibility of the customer.